

**PETROPLAST
JALILVAND.CO**



**петрупдоте жалилванд
компания**

Exclusive Representative of selling shazand

Petrochemical Products in uzbekistan

TECHNICAL SPECIFICATION

Styrene Acrylonitrile (SAN)

<i>Grade</i>	SAN-2
<i>Characteristic</i>	High flow, High transparency.
<i>Application</i>	ABS compounding, office application, cups, cosmetic container, blower fan, pencil case, juicer.

Typical Properties	Test Method	Unit	Typical Value	Spec.
Izod Impact	ASTM D256	Kj/m ²	1	Min 1
MFI (220°C, 10kg)	ASTM D1238	gr/10min	22	19-24
Rockwell Hardness	ASTM D785	M Scale	84	Min 82
HDT	ASTM D648	°C	90	Min 87
Vicat Softening Temp.	ASTM D1525	°C	103	Min 96
Tensile Strength	ASTM D638	kg/cm ²	670	Min 630
Flexural Strength	ASTM D790	kg/cm ²	750	Min 700
Flexural Modulus	ASTM D790	kg/cm ²	31500	Min 31000
Water Absorption	ASTM D570	%	0.3	0.3
Specific Gravity	ASTM D792	-	1.04	1.04
Molding Shrinkage	ASTM D955	%	0.2-0.6	0.2-0.6
Flammability	UI94	-	HB	HB

Central Office: Unit 5, No.10, Sepehr 4 Alley, Sepehr St., Marzdaran Blvd., Zhandarmeri Town, Tehran, Iran.

Telfax: +98 21 4428 4731-2

Mashhad Office: Shahed 50th, Shahed Blvd., Gharb Town, Mashhad, Iran.

Tel.: +985136202400-1

Uzbekistan Tel.: +998 97 404 0929

Website: www.petroplastjalilvand.com

E-mail: info@petroplastjalilvand.com