

**PETROPLAST  
JALILVAND.CO**



**петрупдосте жалилванд  
компания**

Exclusive Representative of selling shazand

Petrochemical Products in uzbekistan

## TECHNICAL SPECIFICATION

### *Acrylonitrile Butadiene Styrene*

<i>Grade</i>	ABS60
<i>Properties</i>	Strong solvent paint.
<i>Application</i>	Electronic and electrical parts, Automobile parts, Refrigerator knobs, Motorcycle parts, house appliances, Cosmetic case.

Typical Properties	Test Method	Test Condition	Unit	Value	Spec.
Izod Impact	ASTM D 256	6.4mm, Notch	kJ/m <sup>2</sup>	25	Min 23
MFI	ASTM D 1238	220°C, 10kg	gr/10min	15	10-20
Rockwell Hardness	ASTM D 785	-	R Scale	112	100-120
HDT	ASTM D 648	1.82MPa	°C	87	Min 85
Vicat Softening Temp.	ASTM D 1525	5kg/50 °C	°C	97	Min 96
Tensile Strength	ASTM D 638	23°C, 50mm/min	kg/cm <sup>2</sup>	455	Min 440
Tensile Elongation	ASTM D 638	23°C, 50mm/min	%	22	Min 20
Flexural Strength	ASTM D 790	23°C, 2.8mm/min	kg/cm <sup>2</sup>	670	Min 650
Flexural Modulus	ASTM D 790	23°C, 2.8mm/min	kg/cm <sup>2</sup>	22000	Min 20000
Specific Gravity	ASTM D 792	23°C	-	1.04	1.04
Molding Shrinkage	ASTM D 955	-	%	0.4-0.7	0.4-0.7
Flamability	UI94	1/8inch (3.2mm)	-	HB	HB

**Central Office:** Unit 5, No.10, Sepehr 4 Alley, Sepehr St., Marzdaran Blvd., Zhandarmeri Town, Tehran, Iran.

**Telfax:** +98 21 4428 4731-2

**Mashhad Office:** Shahed 50<sup>th</sup>, Shahed Blvd., Gharb Town, Mashhad, Iran.

**Tel.:** +985136202400-1

**Uzbekistan Tel.:** +998 97 404 0929

**Website:** www.petroplastjalilvand.com

**E-mail:** info@petroplastjalilvand.com