

**PETROPLAST
JALILVAND.CO**



**петрупдосте жалилванд
компания**

Exclusive Representative of selling shazand

Petrochemical Products in uzbekistan

TECHNICAL SPECIFICATION

Acrylonitrile Butadiene Styrene

| | |
|--------------------|--|
| <i>Grade</i> | ABS70 |
| <i>Properties</i> | Super high impact resistance. |
| <i>Application</i> | Refrigerator interior container and door liner (HCFC-141b blowing agent use), etc. |

| Typical Properties | Test Method | Test Condition | Unit | Value | Spec. |
|-----------------------|-------------|-----------------|--------------------|---------|-----------|
| Izod Impact | ASTM D 256 | 6.4mm, Notch | kJ/m ² | 26 | Min 23 |
| MFI | ASTM D 1238 | 220°C, 10kg | gr/10min | 14 | 8-16 |
| Rockwell Hardness | ASTM D 785 | - | R Scale | 113 | 100-120 |
| HDT | ASTM D 648 | 1.82MPa | °C | 90 | Min 85 |
| Vicat Softening Temp. | ASTM D 1525 | 5kg/50 °C | °C | 100 | Min 96 |
| Tensile Strength | ASTM D 638 | 23°C, 50mm/min | kg/cm ² | 470 | Min 440 |
| Tensile Elongation | ASTM D 638 | 23°C, 50mm/min | % | 25 | Min 18 |
| Flexural Strength | ASTM D 790 | 23°C, 2.8mm/min | kg/cm ² | 670 | Min 650 |
| Flexural Modulus | ASTM D 790 | 23°C, 2.8mm/min | kg/cm ² | 23000 | Min 20000 |
| Specific Gravity | ASTM D 792 | 23°C | - | 1.04 | 1.04 |
| Molding Shrinkage | ASTM D 955 | - | % | 0.4-0.7 | 0.4-0.7 |
| Flamability | UI94 | 1/8inch (3.2mm) | - | HB | HB |

Central Office: Unit 5, No.10, Sepehr 4 Alley, Sepehr St., Marzdaran Blvd., Zhandarmeri Town, Tehran, Iran.

Telfax: +98 21 4428 4731-2

Mashhad Office: Shahed 50th, Shahed Blvd., Gharb Town, Mashhad, Iran.

Tel.: +985136202400-1

Uzbekistan Tel.: +998 97 404 0929

Website: www.petroplastjalilvand.com

E-mail: info@petroplastjalilvand.com