

**PETROPLAST
JALILVAND.CO**



**петрупдоте жалилванд
компания**

Exclusive Representative of selling shazand

Petrochemical Products in uzbekistan

TECHNICAL SPECIFICATION

Low Density Polyethylene - Film

<i>Grade</i>	LF0200
<i>Application</i>	Good clarity film for bags.
<i>*</i>	TSTM = TOYO SODA STANDARD TEST METHOD

Typical Properties	Test Method	Unit	Spec.
MFI (190°C, 2.16kg)	ASTM D1238	gr/10min	1.8-2.2
Density	TSTM* 209B	gr/ml	0.9190-0.9225
Softening Point	ASTM D1525	°C	92-96
Haze	ASTM D1003	%	15 Max
Gloss (60°)	ASTM D523	gu	60 Min
Elongation at Break (MD/TD)	ASTM D882	%	330 Min / 600 Min
Tensile at Break (MD)	ASTM D882	kg/cm ²	160 Min
Dart Impact	ASTM D1709	gr	100 Min

Central Office: Unit 5, No.10, Sepehr 4 Alley, Sepehr St., Marzdaran Blvd., Zhandarmeri Town, Tehran, Iran.

Telfax: +98 21 4428 4731-2

Mashhad Office: Shahed 50th, Shahed Blvd., Gharb Town, Mashhad, Iran.

Tel.: +985136202400-1

Uzbekistan Tel.: +998 97 404 0929

Website: www.petroplastjalilvand.com

E-mail: info@petroplastjalilvand.com