

**PETROPLAST
JALILVAND.CO**



**петрупдосте жалилванд
компания**

Exclusive Representative of selling shazand

Petrochemical Products in uzbekistan

TECHNICAL SPECIFICATION

Low Density Polyethylene - Film

Grade	LH0075
Application	General purpose film for packaging.
*	TSTM = TOYO SODA STANDARD TEST METHOD
**	HDT = HEAD DEFLECTION TEMPERATURE

Typical Properties	Test Method	Unit	Spec.
MFI (190°C, 2.16kg)	ASTM D1238	gr/10min	0.68-0.85
Density	TSTM* 209B	gr/ml	0.9190-0.9225
Vicat Softening Temperature	ASTM D1525	°C	93-97
Elongation at Break (MD/TD)	ASTM D882	%	300 Min / 450 Min
Tensile at Break	ASTM D882	kg/cm ²	170 Min
HDT**	ASTM D648	°C	30-36
Dart Impact	ASTM D1709	gr	120 Min

Central Office: Unit 5, No.10, Sepehr 4 Alley, Sepehr St., Marzdaran Blvd., Zhandarmeri Town, Tehran, Iran.

Telfax: +98 21 4428 4731-2

Mashhad Office: Shahed 50th, Shahed Blvd., Gharb Town, Mashhad, Iran.

Tel.: +985136202400-1

Uzbekistan Tel.: +998 97 404 0929

Website: www.petroplastjalilvand.com

E-mail: info@petroplastjalilvand.com