

**PETROPLAST
JALILVAND.CO**



**петрупдосте жалилванд
компания**

Exclusive Representative of selling shazand

Petrochemical Products in uzbekistan

TECHNICAL SPECIFICATION

Linear Low Density Polyethylene - Blown Film (Innovene licensee)

Grade	LL1209KJ
Application	Lamination film, display packaging, co-extrusion

Typical Properties	Test Method	Unit	Spec.
MFI (190°C, 2.16kg)	D1238/L	gr/10min	0.9
Density	D2839	gr/ml	0.920
Vicat Softening Point, 10N	D1525	°C	100
Tensile Strength at Yield, MD/TD	D638	MPa	9.5/9.5
Elongation at Break, MD/TD	D638	%	450/800
Tensile Strength at Break, MD/TD	D638	MPa	38/28
Tear Strength, MD/TD	D1922	gr/25mic	85/530
Impact Strength, Dart	D1709	gr	150
Haze	D1003	%	5
Gloss (45°)	D2457	Rating	70

Central Office: Unit 5, No.10, Sepehr 4 Alley, Sepehr St., Marzdaran Blvd., Zhandarmeri Town, Tehran, Iran.

Telfax: +98 21 4428 4731-2

Mashhad Office: Shahed 50th, Shahed Blvd., Gharb Town, Mashhad, Iran.

Tel.: +985136202400-1

Uzbekistan Tel.: +998 97 404 0929

Website: www.petroplastjalilvand.com

E-mail: info@petroplastjalilvand.com