

**PETROPLAST
JALILVAND.CO**



**петрупдоте жалилванд
компания**

Exclusive Representative of selling shazand

Petrochemical Products in uzbekistan

TECHNICAL SPECIFICATION

Polypropylene - Fiber

<i>Grade</i>	PY0400
<i>Application</i>	Cloth & food industry, heavy duty woven bags, ropes, strings.

Typical Properties	Test Method	Unit	Spec.
MFI (230°C, 2.16kg)	ASTM D1238	gr/10min	3-5
Vicat Softening Temperature	ASTM D1525	°C	152-156
Tensile Strength	ASTM D638	kg/cm ²	350 Min
Elongation	ASTM D638	%	550 Min
Izod Impact Strength	ASTM D256	Kg.cm/cm	3 Min
Volatile Matter	ASTM D639	%wt	0.05 Max
Ash Content	ASTM D1960	%wt	0.3 Max

Central Office: Unit 5, No.10, Sepehr 4 Alley, Sepehr St., Marzdaran Blvd., Zhandarmeri Town, Tehran, Iran.

Telfax: +98 21 4428 4731-2

Mashhad Office: Shahed 50th, Shahed Blvd., Gharb Town, Mashhad, Iran.

Tel.: +985136202400-1

Uzbekistan Tel.: +998 97 404 0929

Website: www.petroplastjalilvand.com

E-mail: info@petroplastjalilvand.com